

DIMENSIONS

FORMAT	Immenso	
Width	278.5	mm
Length	1380	mm
Number of panels per pack	8	
m² per pack	2.306	m²
Bevels	with pressed in bevel all around	
Thickness	8	mm
Tongue and groove	Uniclic	
Water resistance warranty	10	years

FACTORY WARRANTY

	METHOD	PARAMETERS	Balterio VALUES	
Usage class	EN 13329		Class	21-22-23/31-32
CE	EN 14041	Notified body	NB0766 EPH Dresden	
Warranty	Residential use	See warranty conditions	25	years
	Water resistancy		10	years
	Commercial use	See warranty conditions	5	years

GENERAL DATA (ACCORDING TO EN 13329)

	METHOD	PARAMETERS	NORM REQUIREMENTS		Balterio VALUES	
Wear resistance	EN 13329		≥ 4000	cycles	≥ 4000	cycles
Wear class	EN 13329		AC4		AC4	
Impact resistance	EN 13329	Small ball	≥ 12N		≥ 12N	
		Big ball	≥750mm		≥750mm	
Scratch resistance	EN 438-2, 25		Charge	≥ 3N	Charge	≥ 5N
Effect of a castor chair	ISO 4918 (with underlay)		25000 cycles		No change	
Thickness swelling	ISO 24336	After 24h immersion at 20°C	≤ 18%		≤ 12%	
Locking strength	ISO 24334	Fl0,2 long side	≥ 1 kN/m		≥ 1	kN/m
		Fmax long side			≥ 1	kN/m
		Fs0,2 short side	≥ 2 kN/m		≥ 2	kN/m
		Fmax short side			≥ 2	kN/m
Effect of a furniture leg	EN 424		No damage shall be visible,when tested with foot type 0		No visible damage	
Surface soundness	EN 13329	N/mm²	≥ 1,25		≥ 1,50	
Static indentation	EN 433		residual indentation ≤ 0,05 mm		No visible change	
Resistance to staining	EN 438	Group 1,2	Class	5	Class	5
		Group 3	Class	4	Class	4
General appearance	EN 13329	Height differences	≤ 0,15 mm		≤ 0,10 mm	
		Opening between joints	≤ 0,20 mm		≤ 0,10 mm	
		Cupping in the length	concave ≤ 0,50%		≤ 0,50%	
			convex ≤ 1,00%		≤ 1,00%	
		Cupping in the width	concave ≤ 0,15%		≤ 0,15%	
			convex ≤ 0,20%		≤ 0,20%	
Dimensional variations after changes in relative humidity	EN 13329	δl	δl average ≤ 0,9 mm		≤ 0,9 mm	
		δw	δw average ≤ 0,9 mm		≤ 0,9 mm	
Light fastness	EN ISO 4892-2:2006/A1:2009 procedure B - cycle 5	grey reference	Class	≥ 4	Class	4



OTHER TECHNICAL DATA

	METHOD	PARAMETERS	NORM REQUIREMENTS	Balterio VALUES
Impact sound reduction	ISO 712/2	On a Balterio underlay		$\Delta L_w \approx 20$ dB (Depending on used underlay)
Burning cigarette	EN 438-2,30		Class 4	Class 5

ENVIRONMENT, SAFETY & HEALTH

	METHOD	PARAMETERS	NORM REQUIREMENTS	Balterio VALUES
Formaldehyde emission	EN 717-1	ppm	$E1 < 0,1$	$< 0,01$
Anti-static	EN 1815		$\leq 2,0$ kV	$\leq 2,0$ kV
Reaction to fire	EN 13501-1	Class		Cfl-s1
Thermal resistance	EN 12996:2001	m^2K/W		0.055 m^2K/W
Floor heating		On a Balterio underlay	See special instructions	Suitable
Slip resistance	EN 13893	μ	$\mu \geq 0,30$	DS: $\mu \geq 0,30$

CERTIFICATES

U-zeichen	Z-156.606-996
AFFSET	A+
PEFC	PEFC/07-32-37
M1	
EU Ecolabel	SE/035/001

